



## Rewmar Flexyfix

Ideal for fixing GRP sheet, treads and nosings

- Flexyfix is a solvent and water free, rapid curing, ready to use elastic adhesive and is especially suited to bonding flooring accessories in applications where rapid setting is a requirement.
- Stair nosings can be fixed without the need for mechanical fixings. (Provided the substrate is stable and sound and sufficient adhesive is applied.)
- Flexyfix can be used on all clean, sound and dust free surfaces.
- It is suitable for use on both porous and non-porous surfaces.
- Easy to apply.
- High final bond strength (according to DIN 53504).

## Parts

Part Number	Size	Colour	Weight (kg)
PU45FF	290 ml cartridge	White	0.517

## Technical Specifications

<b>Material</b>	MS Polymer
<b>Min. Operating Temperature</b>	-40°C
<b>Max. Operating Temperature</b>	+90°C
<b>UV Resistance</b>	Yes
<b>Installation Method</b>	The adhesive should be applied by means of a caulking gun with a ratio of 18:1
<b>Cleaning Method</b>	Rewmar wipes immediately after application. Tools can be cleaned prior to curing with Rewmar wipes or mechanically after curing
<b>COO (Country of Origin)</b>	UK
<b>Tensile Strength</b>	> 3.5N/mm <sup>2</sup>
<b>Elongation</b>	>200%

<b>Notes</b>	This product is not suitable for use on Polypropylene, Teflon, Bitumen or Asphalt
<b>Shelf-life</b>	12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°.
<b>Surface preparation</b>	Before application ensure that all surfaces are clean and dust free. There is no requirement to ensure that the surfaces are dry, as this adhesive will work in wet conditions including under water.
<b>Curing system</b>	Moisture curing
<b>Consistency</b>	Paste
<b>Specific gravity (g/cm³)</b>	Approx. 1.5g/mL
<b>Open time at 21°C and 50% R.H</b>	Approx. 5 minutes (This can vary according to environmental circumstances such as temperature, humidity, substrate etc.)
<b>Adjustability time at 21°C and 50% RH</b>	Approx. 5 minutes (This can vary according to environmental circumstances such as temperature, humidity, substrate etc.)
<b>Set to load bearing</b>	Approx. 30 minutes (This can vary according to environmental circumstances such as temperature, humidity, substrate etc.)
<b>Total solids content</b>	100% (solvent free)
<b>Application rate</b>	As an adhesive approx.1.5 m² ( When applied in 10mm bead at 300 mm centres to one surface only.)

Get in touch | To order FREE samples or arrange a site visit please call +44 (0)1788 228 555 or email [sales@cobaeurope.com](mailto:sales@cobaeurope.com)

[www.cobaeurope.com](http://www.cobaeurope.com)